



# Topcoat Mixing Ratios

## 285-60 Primer 4:1:1

**4 - 285-60**

**1 - 929-81/83/84 HARDENER**

**1 - 352-50/91/216 REDUCER**

## 285-60 Sealer

**1 - 285-60**

**1 - 55-Line BASECOAT or 22-Line**

## THEN MIX 2:1:10%-30%

**2 - 285-60 w/ COLOR**

**1 - 929-81/83/84 HARDENER**

**10%-30% - 352-50/91/216 REDUCER**

***Leading Edge***  
Auto Refinishes, Inc.

(480) 966-8819 • (480) 517-9734 FAX