



Topcoat Mixing Ratios

BASECOAT 2:1

2 - BASECOAT

1 - ANY UR REDUCER

DC-76NR TURBO CLEAR 6:1

6 - DC-76NR

1 - DH-42 or DH-46

DC-92 3:1:20%

3 - DC-92

1 - DH-42 or DH-46

20% - ANY UR REDUCER

DC-5100 3:1

3 - DC-5100

1 - DH-14 or DH-16 or DH-18

DC-5300 3:1:1

3 - DC-5300

1 - DH-42 or DH-46 or DH-47

1 - ANY UR REDUCER

UNO 4:1:1

4 - UNO

1 - DH-42 or DH-46

1 - ANY UR REDUCER

BLENDING METALLIC BASECOATS

BC-100 1:1 WITH UR REDUCER

ADD 1:1 WITH REDUCED COLOR

Leading Edge
Auto Refinishes, Inc.

(480) 966-8819 • (480) 517-9734 FAX